



# DuraForm<sup>®</sup> HST Composite

Selective Laser Sintering (SLS)

A fiber-reinforced material with an ideal mix of stiffness, strength and high temperature resistance.

## General Properties

MEASUREMENT	CONDITION	METRIC	U.S.
Specific Gravity	ASTM D792	1.20 g/cm <sup>3</sup>	1.20 g/cm <sup>3</sup>

## Mechanical Properties

MEASUREMENT	CONDITION	METRIC	U.S.
Tensile Strength Ultimate (MPa   psi)	ASTM D 638	48–51	7050–7350
Tensile Modulus (MPa   psi)	ASTM D 638	5475–5725	795–831
Elongation at Break (%)	ASTM D 638	4.5	4.5
Flexural Strength, Ultimate (MPa   psi)	ASTM D 790	83–89	12000–12900
Flexural Modulus (MPa   ksi)	ASTM D 790	4400–4550	638–660
Hardness, Shore D	ASTM D2240	75	75
Impact Strength (J/m   ft-lb/in) (notched Izod, 23°C)	ASTM D256	37.4	0.7
Impact Strength (J/m   ft-lb/in) (unnotched Izod, 23°C)	ASTM D256	310	5.8
Gardner Impact (J   ft-lb)	ASTM D5420	5	3.7

Data was generated by building parts using 100% virgin powder under typical default parameters. DuraForm HST Composite was processed on a Sinterstation<sup>®</sup> HiQ™ + HS SLS System at 25 watts laser power, 10 m/sec [400 inches/sec] scan speed, and a powder layer thickness of 0.1 mm [0.004 inches].

## Features

- High specific stiffness
- Elevated temperature resistance
- Anisotropic mechanical properties just like fiber-filled, injection molded materials
- Non-conductive and RF transparent
- Easy-to-finish surface

## Benefits

- Functional prototypes can be tested in “real life” environments
- Complex end-use parts can be economically manufactured in low-to-medium volumes
- Excels in load-bearing applications at higher temperatures
- Attractive surface finish

## Applications

- Complex, thin-wall ductwork
- Functional prototypes that approach end-use performance properties
- Appropriate for low- to mid-volume rapid manufacturing
- Medical applications requiring USP Class VI compliance, or biocompatibility
  - Motorsports
  - Aerospace
- Housing and enclosures
- Impellers and connectors
- Consumer sporting goods
- Vehicle dashboards and grilles
- Snap-fit designs
- Parts requiring machining or joining with adhesives



# DuraForm® HST Composite

Selective Laser Sintering (SLS)

A fiber-reinforced material with an ideal mix of stiffness, strength and high temperature resistance.

## Thermal Properties

MEASUREMENT	CONDITION	METRIC	U.S.
Heat Deflection Temperature	ASTM D 648 @ 0.45 MPa @ 1.82 MPa	184 °C 179 °C	363 °F 355 °F
Coefficient of Thermal Expansion ( $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$ / $\mu\text{m}/\text{in}\cdot^{\circ}\text{F}$ )	ASTM E 831 0-50 °C 85-145 °C	138.3 267.2	76.8 148.4
Specific Heat Capacity ( $\text{J}/\text{g}\cdot^{\circ}\text{C}$   $\text{BTU}/\text{lb}\cdot^{\circ}\text{F}$ )	ASTM E1269	1.64	0.392
Thermal Conductivity ( $\text{W}/\text{m}\cdot\text{K}$   $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot^{\circ}\text{F}$ )	ASTM E1225	0.29	2.0
Flammability	UL 94	HB	HB

## Electrical Properties

MEASUREMENT	CONDITION	METRIC	U.S.
Volume Resistivity (ohm-cm)	ASTM D257	$6.7 \times 10^{15}$	$6.7 \times 10^{15}$
Surface Resistivity (ohm)	ASTM D257	$5.2 \times 10^{15}$	$5.2 \times 10^{15}$
Dissipation Factor, 1 KHz	ASTM D150	0.028	0.028
Dielectric Constant, 1 KHz	ASTM D150	3.14	3.14
Dielectric Strength (kV/mm   kV/in)	ASTM D149	18.5	470

Data was generated by building parts using 100% virgin powder under typical default parameters. DuraForm HST Composite was processed on a Sinterstation® HiQ™ + HS SLS System at 25 watts laser power, 10 m/sec [400 inches/sec] scan speed, and a powder layer thickness of 0.1 mm [0.004 inches].



[www.3dsystems.com](http://www.3dsystems.com)

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2020 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. 3D Systems, the 3D Systems logo, DuraForm, and Sinterstation are registered trademarks and HiQ is a trademark of 3D Systems, Inc.